

SeaRox SL 740



Marine Batts 45

Comfort Insulation

Product description

SeaRox SL 740 is a semi-rigid, resilient slab made of stone wool. The product can be supplied with reinforced alu foil or glass cloth.

Application

SeaRox SL 740 is used for comfort insulation and form part of approved A-30 Deck and A-30 Bulkhead constructions.



Product Properties

	Performance			Norm
	T [°C]	10	50	
Thermal conductivity	λ (W/mK)	0,034	0,039	EN 12667
Nominal density	45 kg/m ³			EN 1602 / IMO
Compressive strength	-			EN 826
Fire classification	Non-combustible Approved for A constructions Low Flame-Spread Properties			Acc. IMO FTP code
Water absorption (short term)	< 1 kg/m ²			EN 1609 AC
Max. Application Temperature	Wool 250°C Facing 80°C			-
Sound absorption directly mounted	$\alpha_w = 0,75$ Thickness: 50 mm			ISO 354 (approximated) Evaluated after ISO 11 654
Facings (on request)	Reinforced alu foil White glass cloth 210 g/m ² (GW 200)			IMO A.653(16) (low flame - spread)

Dimensions

SeaRox SL 740

Thickness (mm): 25-100 Length (mm): 1000 Width (mm): 600


SeaRox SL 740 ALU

Thickness (mm): 25-100 Length (mm): 1000 Width (mm): 600

SeaRox SL 740 GW200

Thickness (mm): 25, 30, 50 Length (mm): 1000 Width (mm): 600

Local variations in standard dimensions might occur.



Rockwool Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.