SeaRox SL 970



Thermal Insulation

Product description

SeaRox SL 970 is a semi-rigid slab made of stone wool.

Application

SeaRox SL 970 is primarily used as high temperature insulation. Furthermore the products can be used as insulation of structures where the temperature exceeds 250°C.

Product Properties


	Performance				Norm
Thermal conductivity	T (°C)	10	100	300	EN 12667
	λ (W/mK)	0,035	0,045	0,084	
Nominal density	110 kg/m ³				EN 1602 / IMO
Compressive strength	-				EN 826
Fire classification	Non-combustible Low Flame-Spread Properties				Acc. IMO FTP code
Water absorption (short term)	< 1 kg/m ²				EN 1609 AC
Max. Application Temperature	Wool: 750°C				-
Sound absorption directly mounted	-				ISO 354 (approximated) Evaluated after ISO 11 654
Facings (on request)	-				IMO A.653(16) (low flame - spread)

Dimensions

 SeaRox SL 970

 Thickness (mm): 25,50 mm
 Length (mm): 1000 mm
 Width (mm): 600 mm

Local variations in standard dimensions might occur.



Rockwool Technical Insulation reservestherighttomakenecessary productchangesatanytime.Technical specifications are thus stated subject to change.

Rockwool Technical Insulation DK-2640 Hedehusene Tel: +45 46 56 16 16 Fax. +45 46 56 16 04 export@rockwool.com www.rockwool-rti.com Part of Rockwool International A/S

